

	Unconfined Compressive Strength of Hydraulically Bound Mixtures			Job Ref	A190707
				Sediment Ref	Val-007
Site Name	Hornsey Gas Works			Mix Design	5% CEMI
Soil Description	Dark grey/brown silty sandy fill with aggregate & brick gravel sized particles			Depth	0.00
Specimen Test Age	7 day	Specimen Depth	m	Sample Type	BLK
Specimen Description				KeyLAB ID	CEGL202009098
Test Method	BS EN 13286:Part 41:2003			Date of test	17/09/2020

Test Number

Length

Diameter

Bulk Density

Moisture Content

Dry Density

Rate of Strain

At failure

Axial Strain

Unconfined Compressive Strength

Mode of Failure

1

93.9

mm

103.4

mm

1.95

Mg/m3

%

Mg/m3

%/min

3.5


%

2411

kPa

Brittle

Axial Compressive Stress v Axial Strain



Remarks

Axial compressive stress corrected for area change, and membrane effects (if used)



CE Geotech Ltd
CEG Laboratories
Matlock Road, Kelstedge
Derbyshire. S45 0DX

General remarks

Approved

Chris Salt

01/10/2020