

Project No. A190707
 Project ID Hornsey Gas Works
 Client Keltbray



CBR Swell Monitoring

BS 1377-4 / BS EN 13286-47

Sample ID	Val-005	
Compaction Method	Vibrating Hammer	
Curing period	4	days

Mould Mass (g)	376.5	g
Mold Diameter (mm)	152.0	mm
Mould Hieght (mm)	126.5	mm
Mass of Mould + Specimen (g)	4300.0	g
Mass of Base Plate (g)	253.5	g
Initial Soaking Time (days)	/	days
Water Appeared at Surface (days)	/	days
Final Mass of Specimen + Mould + Base Plate (g)	4494.5	g

	Tray	Wet	Dry	
Final Moisture Content	-	-	-	g


Swell Measurement Readings

Initial at 0 days	5.00	mm
After Soaking Time	5.02	mm
7 days	5.04	mm
10 days	5.05	mm
14 days	5.07	mm
21 days	5.04	mm
28 days	5.06	mm

CBR Swell Monitoring

BS 1377-4 / BS EN 13286-47

Sample ID Val-005



CBR after 28 days Soaking

177 %

Moisture Content after 28 days Soaking

N/A %

Bulk Density

1.755 Mg/m³

Dry Density

N/A Mg/m³

Veritcal Swell

0.06 mm

Volumetric Swell

0.039 %