

Project No. A190707
 Project ID Hornsey Gas Works
 Client Keltbray



CBR Swell Monitoring

BS 1377-4 / BS EN 13286-47

Sample ID	Val-003	
Compaction Method	Vibrating Hammer	
Curing period	4	days

Mould Mass (g)	375.0	g
Mold Diameter (mm)	152.0	mm
Mould Hieght (mm)	115.5	mm
Mass of Mould + Specimen (g)	4267.5	g
Mass of Base Plate (g)	251.0	g
Initial Soaking Time (days)	/	days
Water Appeared at Surface (days)	/	days
Final Mass of Specimen + Mould + Base Plate (g)	4548.0	g

	Tray	Wet	Dry	
Final Moisture Content	-	-	-	g


Swell Measurement Readings

Initial at 0 days	4.88	mm
After Soaking Time	4.84	mm
7 days	5.51	mm
10 days	5.66	mm
14 days	5.73	mm
21 days	5.76	mm
28 days	5.76	mm

CBR Swell Monitoring

BS 1377-4 / BS EN 13286-47

Sample ID Val-003



CBR after 28 days Soaking

20 %

Moisture Content after 28 days Soaking

N/A %

Bulk Density

1.908 Mg/m³

Dry Density

N/A Mg/m³

Veritcal Swell

0.88 mm

Volumetric Swell

0.579 %