

Project No. A190707
 Project ID Hornsey Gas Works
 Client Keltbray



CBR Swell Monitoring

BS 1377-4 / BS EN 13286-47

Sample ID	Val-006	
Compaction Method	Vibrating Hammer	
Curing period	4	days

Mould Mass (g)	370.5	g
Mold Diameter (mm)	152.0	mm
Mould Hieght (mm)	121.4	mm
Mass of Mould + Specimen (g)	5449.5	g
Mass of Base Plate (g)	261.0	g
Initial Soaking Time (days)	/	days
Water Appeared at Surface (days)	/	days
Final Mass of Specimen + Mould + Base Plate (g)	4595.0	g

	Tray	Wet	Dry	
Final Moisture Content	-	-	-	g


Swell Measurement Readings

Initial at 0 days	6.00	mm
After Soaking Time	6	mm
7 days	6.03	mm
10 days	6.07	mm
14 days	6.10	mm
21 days	6.10	mm
28 days	6.11	mm

CBR Swell Monitoring

BS 1377-4 / BS EN 13286-47

Sample ID Val-006



CBR after 28 days Soaking

64 %

Moisture Content after 28 days Soaking

N/A %

Bulk Density

2.367 Mg/m³

Dry Density

N/A Mg/m³

Veritcal Swell

0.11 mm

Volumetric Swell

0.072 %